



Caratteristiche tecniche

27 CM 4,0	30 CM 4,3	30 AU 4,0	40 RC 5,2
-----------------	-----------------	-----------------	-----------------

DENSITÀ UNI EN ISO 845	3kg/m 3 ± 5%		27	30	30	40
RESISTENZA ALLA COMPRESSIONE UNI EN ISO 3386	kpa ± 15%	40%	4,0	4,3	4,0	5,2
RESISTENZA ALL’AFFONDAMENTO UNI EN ISO 2439	Newton ± 15%	25%	110	120	115	160
		65%	300	330	315	384
ALLUNGAMENTO UNI EN ISO 1798	% min		129	138	144	122
CARICO ALLA ROTTURA (TRAZIONE) UNI EN ISO 1798	kpa min		88	97	100	101
RESILIENZA UNI EN ISO 8307	% (± 10%)		40	33	34	40
PERDITA PORTANZA A FATICA DINAMICA UNI EN ISO 3385	% max		29	29	30	22
DEFORMAZIONE PERMANENTE UNI EN ISO 1856/A	% max	50%	4	4	4	2
		75%	7	8	8	4
CERTIFICATI DI RESISTENZA AL FUOCO			C E M	C E M	C E G	C E M
COLORE						
LARGHEZZA BLOCCO IN CM			215	215	215	215